



FAST-SETTING SOLVENT-FREE ADHESIVE IN WATER DISPERSION WITH LOW WATER CONTENT FOR BONDING WOODEN FLOORING



PRODUCT DESCRIPTION

DCI Parquet 40 is a beige, non-flammable, fast drying, ready-to-use, solvent free dispersion adhesive used for interior installations wooden floors. The product is easy applicable and has good elasticity in order to resist to hygrometric movement of the wood and thermal expansion of substrate. Due to content of special additives the product is resistant to bacteria and mold.

FIELD OF APPLICATION

- For interior use
- For installation of wooden parquet
- For installation of industrial parquet
- For installation of wooden floorboards
- For installation of wooden parquet on heated floor

SUITABLE SUBSTRATES

- Concrete floor
- Cement screed
- Chipboard panels
- Wooden substrate

LIMITATIONS

- Not to be used over tile substrates.
- Not to be used on non-absorption substrates. The adhesive cures through evaporation of its water content.
- Not to be used for big dimensions wooden parquets.

- Not to be used at temperatures below 8°C.
- Not to be used for exterior application.
- Not to be used in areas subject to constant water exposure, immersion, or hydrostatic pressure.
- Not to be used in commercial showers, steam rooms, fountains, or submerged applications.
- Not to be used on a metal substrate.
- Not to be used on anhydrite substrates.
- Protect from the frost.
- Not to be used on screed with high moisture content.

APPLICATION PROCEDURE

a) Preparation of the support

The substrates must be cured and sufficiently dry, mechanically strong, free from loose particles, grease, oils, paint, wax, etc. The cement substrates must not be subject to shrinkage after installing the wood. The moisture content of the screed must be lower than the maximum prescribed by the parquet manufacturer. It is necessary to check moisture content throughout the entire thickness of the substrate, using a carbide hygrometer. During spring and summer, renders must be cured for at least one week for every centimeter of thickness, and cement screeds must be cured for at least 28 days unless they have been made with

DCI special binders for screeds such as Screed 80, Level S10, or with Level S30. In case of floating screeds over insulation or light weight layers and slabs on grade must be provided with a vapour barrier to prevent rising damp.

b) Preparing the product

DCI Parquet 40 is ready to use the product but is suggested to mix the adhesive for homogenization.

c) Applying the product

Apply DCI Parquet 40 to the substrate using a notched trowel suitable to the format. The open time of the product is maximum 30 minutes under normal temperature and humidity conditions, which must be taken into consideration when spreading the adhesive. If a skin forms, the adhesive must be removed and replaced.

d) Installing the tiles

The parquet to be installed has to be stored in a dry area, on shelter and not to be subject to vapour condensation. The parquet must be insulated from the ground. Before installing, check that the moisture level in the wood and the ambient humidity are as prescribed by the manufacturer. Press the wood parquet firmly into the wet DCI Parquet 40 to ensure good contact. When installing the parquet leave an expansion joint of approximately 1 cm around the perimetral, columns, and any elements crossing the floor. Do not bond edges of wood strips together.

COVERAGE / CONSUMPTION

Approximately 0.6-1 kg/m² according to the notched trowel

PACKAGING

DCI Parquet 40 is supplied in:

- 15 kg plastic bucket.
- 5 kg plastic bucket.

SHELF LIFE

Original sealed packaging of this product is guaranteed to be of first quality for 24 months if stored in a dry area. In places with high humidity, the shelf life of the bagged product will be reduced.

SAFETY INSTRUCTION

DCI Parquet 40 is not considered dangerous according to the European regulation regarding the classification of mixtures. It is suggested to wear protective clothing and take the usual precautions taken to handle chemicals. For further information about the safe use of our product, please refer to the latest version of our Material Safety Data Sheet. **PRODUCT FOR PROFESSIONAL USE.**

TECHNICAL DATA

Product identity	
Consistency:	Pasty
Color:	Beige
Bulk density (kg/m ³):	1400
Viscosity:	220,000 (Rpm 5, Spindle 7)
Dry solids content (%):	75
Application data (at +23°C and 50% R.H.)	
Mix ratio:	Ready to use
Consistency of mix:	very pasty
pH of mix:	12
Application temperature:	+5°C to +40°C
Open time (according to EN 1346):	>30 minutes
Adjustability time:	approx. 40 minutes
Polishing:	After 7 Days
Final performances	
Bonding strength:	3.7 N/mm ²
Temperature resistance after final cure:	from -20°C to +90°C

WARNING

Danger. Contains Portland Cement: Chromium VI < 2 ppm within the validity period of the product. H315 Causes skin irritation. H317 May cause an allergic skin reaction. H318 Causes serious eye damage. H335 May cause respiratory irritation. P261 Avoid breathing dust. P280 Wear protective gloves/protective clothing/eye protection/face protection. P302 + P352 IF IN CONTACT WITH YOUR SKIN: Wash with plenty of water/... P305 + P351 + P338 IF IN CONTACT WITH YOUR EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. P310 Immediately call a POISON CENTER/doctor/...



+1 55 12 258 428
info@dc-industries.us
www.dc-industries.us