

SPECIFICATIONS

PU 300

Is a highly deformable, low modulus of elasticity, thixotropic sealant. PU 300 sets progressively by reacting with the water vapour in the air or in the pores in the substrate to form elastic, deformable rubber that adheres to the substrate. Once set, it compensates for compressive, tensile and torsional movements in joints while guaranteeing high resistance to punching and surface friction. PU 300 is resistant to dry service temperatures of -30°C to +80°C.

TECHNICAL DATA

Product identity

Consistency: thixotropic paste

Color: grey

Density (kg/m³): 1450

Viscosity (mPa.s): 1,200,000

Dry solids content (%): 100